TECHNICAL DATA SHEET





Typical Analysis

	Typical BGC Range	AS 1316	Units
Mortar Compressive Strengths			
7 day	24.4 – 25.6	Min. 10	(MPa)
28 day	28.7 – 31.5	Min. 15	(MPa)
Vicat Setting Time			
Normal Consistency	-	-	(%)
Initial Set	75 – 105	Min. 75	(minutes)
Final Set	135 - 150	Max. 720	(minutes)
	_		
Chemical Analysis			
SO ₃	2.8 – 2.8	Max. 3.5	(%)
Loss on Ignition	7.6 – 8.0	-	(%)

Note: Typical range is at 95% confidence level, individual results may be outside of this range.

Issue Date: 30 March 2023